

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **07165868 A**

(43) Date of publication of application: **27.06.95**

(51) Int. Cl.

C08G 18/65

C08G 18/65

C08G 18/65

C08G 77/458

(21) Application number: **05344063**

(22) Date of filing: **16.12.93**

(71) Applicant: **SANYO CHEM IND LTD**


(72) Inventor: **KOBAYASHI YOSHIO
MURAHASHI TOMOYUKI
AKIYAMA HAJIME**

(54) PREPARATION OF POLYURETHANE RESIN

(57) Abstract:

PURPOSE: To obtain a polyurethane excellent in highly stretching properties, friction resistance to metals and thermosetting properties by incorporating a given amount of a specific diol in a polymeric diol in the preparation of the polyurethane by reacting the polymeric diol, an organic diisocyanate and a chain extender.

CONSTITUTION: In the preparation of a polyurethane by reacting a polymeric diol (e.g. polycaprolactonediol), an organic diisocyanate (e.g. 4,4'-diphenylmethane diisocyanate) and a chain extender (e.g. 1,4-butanediol), 1-30wt.% of a siliconediol given by the formula (wherein R is a 2-3 C alkylene; m is 1-3; and n is 1-100) is incorporated in the polymeric diol.



COPYRIGHT: (C)1995,JPO